

DIAREX H370

High Impact Polystyrene Resin

Special Characteristics: H370 is the good flow and high impact polystyrene. It gives good mechanical properties while providing with easy process ability and short cycle time.

Typical Applications: Food container, Home appliance

Typical Properties:

Properties	DIAREX H370	Unit	Test Method
Physical Properties			
Melt Flow Rate (200 °C, 5 kg)	5.0	g/10 min	ASTM D1238
Density	1.04	g/cm ³	ASTM D792
Vicat Softening Point	100	°C	ASTM D1525
Deflection Temperature	74	°C	ASTM D648
Mechanical Properties			
Tensile Strength at Yield	4,000	lb/in ²	ASTM D638
Tensile Elongation	40	%	ASTM D638
Flexural Strength	6,500	lb/in ²	ASTM D790
Flexural Modulus (x10,000)	33	lb/in ²	ASTM D790
Izod Impact Strength	2.3	ft.lb/in	ASTM D256
Rockwell Hardness	R112	Scale	ASTM D785
Underwriter Laboratory*	HB (1.5 mm)		UL-94

*Data based on injection molding test pieces.

Recommendation:

DIAREX H370 can be processed with recommended temperature between 190 – 240 °C and mold temperatures between 30 and 70 °C. Melt temperature should not exceed 260 °C.

Note: Modifications of the processing conditions based on the variations of the product design and machine configuration.

