

EMERGE™ PC 8600E85-10

Advanced Resin

Overview

EMERGE™ PC 8600E85-10 Advanced Resin contains 85% post-consumer recycled (PCR) polycarbonate. This ignition resistant PC does not contain chlorinated, brominated or phosphate flame retardant additives to comply with global environmental standards. This resin combines good mechanical, thermal, and chemical properties while retaining excellent processability.

Applications

- Electronics and electrical appliances
- Charger and adaptor enclosures
- Information technology equipment

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm ³	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 g/10 min	10 g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus ¹	334000 psi	2300 MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield	8700 psi	60.0 MPa	
Break	9430 psi	65.0 MPa	
Tensile Elongation ²			ASTM D638
Yield	6.0 %	6.0 %	
Break	120 %	120 %	
Flexural Modulus ³	348000 psi	2400 MPa	ASTM D790
Flexural Strength ³	13800 psi	95.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	14 ft-lb/in	750 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
264 psi (1.8 MPa), Unannealed	259 °F	126 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	257 °F	125 °C	ISO 75-2/A
Vicat Softening Temperature	302 °F	150 °C	ISO 306/A120 ASTM D1525 ⁴
Ball Indentation Temperature	> 257 °F	> 125 °C	IEC 60335-1
CLTE - Flow (-40 to 176°F (-40 to 80°C))	3.6E-5 in/in/°F	6.5E-5 cm/cm/°C	ASTM D696
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity	1.0E+17 ohms-cm	1.0E+17 ohms-cm	ASTM D257
Dielectric Strength	560 V/mil	22 kV/mm	ASTM D149
Arc Resistance	PLC 7	PLC 7	ASTM D495

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating ⁵			UL 94
0.016 in (0.40 mm)	HB	HB	
0.022 in (0.55 mm)	V-2	V-2	
0.04 in (1.0 mm)	V-1	V-1	
0.06 in (1.4 mm)	V-0	V-0	
0.10 in (2.5 mm)	V-0	V-0	
0.12 in (3.0 mm)	V-0	V-0	
Glow Wire Flammability Index ⁵			IEC 60695-2-12
0.08 in (2.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature ⁵			IEC 60695-2-13
0.08 in (2.0 mm)	1470 °F	800 °C	
Oxygen Index ⁵	35 %	35 %	ISO 4589-2
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	248 °F	120 °C	
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr	
Processing (Melt) Temp	518 to 572 °F	270 to 300 °C	
Mold Temperature	158 to 230 °F	70 to 110 °C	