

HD7200B

High Density Polyethylene Resin

Special Characteristics : InnoPlus HD7200B is extra high molecular weight high density polyethylene blow molding grade which is recommended for 20-120 litre drums. It has excellent processability and exhibits very high impact strength, stiffness and extremely environment stress crack resistance.

Typical Applications : Hazardous chemical drums, Agricultural chemical drums.

Typical Properties :

Properties	HD7200B	Unit	Test Method
Physical Properties			
Melt Flow Rate (190 °C, 2.16 kg)	0.05	g/10 min	ASTM D1238
Melt Flow Rate (190 °C, 21.6 kg)	8.5	g/10 min	ASTM D1238
Density	0.956	g/cm ³	ASTM D1505
Vicat softening point	124	°C	ASTM D1525
Melting Temperature	134	°C	ASTM D3418
Mechanical Properties (Based on com-pression specimens)			
Tensile Strength at Yield	300	kg/cm ²	ASTM D638
Tensile Strength at Break	350	kg/cm ²	ASTM D638
Elongation at Break	800	%	ASTM D638
Stiffness	10,000	kg/cm ²	ASTM D747
Flexural Modulus	12,000	kg/cm ²	ASTM D790
Notched Izod Impact Strength	25 (NB)*	kg.cm/cm	ASTM D256
Durometer Hardness	63	Shore D	ASTM D2240
ESCR, F ₅₀ (Condition B, 25 % Igepal)	>1000	hrs	ASTM D1693

* NB = Non Break

Recommendation :

Extruder temperature : 195 - 220 °C

Die temperature : 200 - 220 °C

FDA Statement :

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.