LL7410G1

Linear Low Density Polyethylene Resin

Special Characteristics: InnoPlus LL7410G1 resin is a linear low density polyethylene with butene comonomers, with low content of slip and antiblock added. Films extruded from InnoPlus LL7410G1 has extremely low gel level with superior clarity. This grade offers high tensile strength, elongation, good toughness and outstanding puncture strength.

Typical Applications: InnoPlus LL7410G1 is recommended for producing the lamination films, general purpose films, liners, food packaging, heavy duty and agricultural films.

Additives: Slip 400 ppm and Antiblock 1500 ppm

Typical Properties:

Properties	LL7410G1	Unit	Test Method
Physical Properties (Based on pellets and press-molded sheet)			
Melt Flow Rate (190 °C, 2.16 kg)	1.0	g/10 min	ASTM D1238
Density	0.920	g/cm^3	ASTM D792
Melting Temperature	121	°C	ASTM D3418
Vicat Softening Point	101	°C	ASTM D1525
Film Properties* (Based on blown film)			
Tensile Strength at Break (MD/TD)	35 / 30	MPa	ASTM D882
Elongation at Break (MD/TD)	700 / 850	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	225 / 240	MPa	ASTM D882
Dart Impact Strength	105	g	ASTM D1709
Tear Strength (MD/TD)	150 / 300	g	ASTM D1922
Haze	15	%	ASTM D1003
Gloss (45°)	38	-	ASTM D2457

** Film made on blown film line at blow up ratio 2.5. Gloss (45□) obtained from 40 microns film while other film properties obtained from 25 microns film.*

Recommendation:

The recommended temperature setting is in the range of 160 – 180 °C for extruder and 170 – 190 °C for die zone.

FDA Statement:

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

[HongKong] +852-69575415 [China GuangDong] +135-3858-6433 [China ShangHai] +188-1699-6168