

TECHNICAL DATA SHEET

LURANYL[®] HT 190

ROMIRA

PPE/PA, injection moulding grade, high heat resistance

PROPERTY	Test Method	Condition	Unit	Value*
----------	-------------	-----------	------	--------

MECHANICAL.....

Tensile Modulus	DIN EN ISO 527	1 mm/min 23 °C	MPa	2,050
Tensile Strength	DIN EN ISO 527	50 mm/min 23 °C	MPa	50
Elongation at Break	DIN EN ISO 527	50 mm/min 23 °C	%	90
Flexural Modulus	DIN EN ISO 178	2 mm/min 23 °C	MPa	-
Flexural Strength	DIN EN ISO 178	2 mm/min 23 °C	MPa	81
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm 23 °C	kJ/m ²	45
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm -30 °C	kJ/m ²	12
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm 23 °C	kJ/m ²	n.b.
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm -30 °C	kJ/m ²	n.b.

PHYSICAL.....

Density	DIN EN ISO 1183	23 °C	g/cm ³	1.05
Water Absorption	DIN EN ISO 62	23 °C, 50 % RH, 24 h	%	0.4

THERMAL.....

Heat deflection temperature (HDT/A)	DIN EN ISO 75-1	1,8 MPa	°C	120
Vicat Softening Temperature (B 50)	DIN EN ISO 306	50 N, 50 °C/h	°C	180
Melt Volume-Flow Rate (MVR)	DIN EN ISO 1133	280 °C, 5 kg	cm ³ /10 min	20
Thermal Coefficient of Linear Expansion	ISO 11359-2	23 °C - 80 °C	10 ⁻⁴ · K ⁻¹	0.95
Processing Shrinkage	DIN EN ISO 294-4	23 °C	%	0.9 - 1.1
Flammability (own test)	UL94	1.5 mm	--	HB