

PULSE™ 979
PC/ABS Engineering Resin

Overview

PULSE™ 979 is a high performance, 10% glass filled PC/ABS resin. The high stiffness and easy processability makes PULSE 979 ideal for complicated parts which require a high dimensional stability. Typical applications are automotive instrument panels.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.18 g/cm ³	1.18 g/cm ³	ISO 1183/B
Apparent (Bulk) Density	0.68 g/cm ³	0.68 g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	10 g/10 min	10 g/10 min	ISO 1133
Molding Shrinkage	3.0E-3 to 5.0E-3 in/in	0.30 to 0.50 %	ISO 294-4
VOC Content	9.00 µg/g	9.00 µg/g	VDA 277
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	653000 psi	4500 MPa	ISO 527-2/1
Tensile Stress (Yield)	11000 psi	76.0 MPa	ISO 527-2/50
Tensile Strain (Yield)	3.0 %	3.0 %	ISO 527-2/50
Flexural Modulus ¹	595000 psi	4100 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	2.9 ft·lb/in ²	6.0 kJ/m ²	
73°F (23°C)	4.3 ft·lb/in ²	9.0 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	271 °F	133 °C	ISO 306/B50
CLTE - Flow (-22 to 176°F (-30 to 80°C))	2.7E-5 in/in/°F	4.9E-5 cm/cm/°C	ISO 11359-2
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	221 °F	105 °C	
Drying Time	4.0 hr	4.0 hr	
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C	
Mold Temperature	158 to 194 °F	70 to 90 °C	