

Technical Data Sheet



ROMILOY® 1035/04 F

PC/ABS-Blend, Injection moulding grade, easy-flowing

<i>Properties</i>	<i>Unit</i>	<i>Test Method</i>	<i>Test Condition</i>	<i>Value*</i>
Mechanical				
Tensile Modulus	MPa	DIN EN ISO 527	23°C 1 mm/min	2,100
Tensile Strength	MPa	DIN EN ISO 527	23°C 50 mm/min	52
Elongation at Break	%	DIN EN ISO 527	23°C 50 mm/min	> 30
Flexural Modulus	MPa	DIN EN ISO 178	23°C 2 mm/min	2,000
Flexural Strength	MPa	DIN EN ISO 178	23°C 2 mm/min	75
Notched Impact Strength (Charpy)	kJ/m ²	DIN EN ISO 179/1eA	80 x 10 x 4 mm 23°C / -30°C	45 / 30
Impact Strength (Charpy)	kJ/m ²	DIN EN ISO 179/1eU	80 x 10 x 4 mm 23°C / -30°C	n.b. / n.b.
Physical				
Density	g/cm ³	DIN EN ISO 1183	23°C, 50% RH	1.14
Water Absorption	%	DIN EN ISO 62	23°C, 24 h	0.2
Thermal				
Heat Distortion Temperature A	°C	DIN EN ISO 75/1	1.8 MPa	106
Vicat Softening Temperature B 50	°C	DIN EN ISO 306	50 N 50°C/h	125
Melt Mass Flow Rate (MFR)	g/10 min	DIN EN ISO 1133	260°C, 5 kg	28
Thermal Conductivity	W/(K·m)	DIN 52612	--	-
Thermal Coefficient of Linear Expansion	10 ⁻⁴ · K ⁻¹	ISO 11359-2	23°C - 55°C	0.85
Processing Shrinkage	%	DIN EN ISO 294-4	23°C	0.4 - 0.7
Flammability (own testing)	--	UL94	1.6 mm	HB
Burning Rate	mm/min	DIN 75200	3.0 mm	< 100

* = These are average figures, which could vary in each production batch due to addition of pigments, antistatica, slip, uv stabilizer or other.

ROMIRA GMBH