

# TECHNICAL DATA SHEET

## ROMILOY<sup>®</sup> 1035/07 GF10

# ROMIRA

PC/ABS, injection moulding grade, 10% glass fibre reinforced, easy-flowing

PROPERTY	Test Method	Condition	Unit	Value*
----------	-------------	-----------	------	--------

### MECHANICAL.....

Tensile Modulus	DIN EN ISO 527	1 mm/min 23 °C	MPa	4,250
Tensile Strength	DIN EN ISO 527	5 mm/min 23 °C	MPa	78
Elongation at Break	DIN EN ISO 527	5 mm/min 23 °C	%	7
Flexural Modulus	DIN EN ISO 178	2 mm/min 23 °C	MPa	4,150
Flexural Strength	DIN EN ISO 178	2 mm/min 23 °C	MPa	111
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm 23 °C	kJ/m <sup>2</sup>	-
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm 23 °C	kJ/m <sup>2</sup>	37
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm -30 °C	kJ/m <sup>2</sup>	26

### PHYSICAL.....

Density	DIN EN ISO 1183	23 °C, 50 % RH	g/cm <sup>3</sup>	1.22
Water Absorption	DIN EN ISO 62	23 °C, 50 % RH, 24 h	%	0.2

### THERMAL.....

Heat deflection temperature (HDT/A)	DIN EN ISO 75-1	1,8 MPa	°C	108
Vicat Softening Temperature (B 50)	DIN EN ISO 306	50 N, 50 °C/h	°C	125
Melt Mass-Flow Rate (MFR)	DIN EN ISO 1133	260 °C, 5 kg	g/10 min	25
Processing Shrinkage	DIN EN ISO 294-4	23 °C	%	0.2 - 0.6
Flammability (own test)	UL94	1.5 mm	--	HB

ROMIRA GMBH