

# TECHNICAL DATA SHEET

## ROMILOY<sup>®</sup> 4010/02 UV GF8

# ROMIRA

PA/ABS, extrusion and injection moulding grade , 8% glass fibre reinforced, UV stabilized

PROPERTY	Test Method	Condition	Unit	Value*	
----------	-------------	-----------	------	--------	--

MECHANICAL.....				Dry as molded	conditioned
Tensile Modulus	DIN EN ISO 527	1 mm/min 23 °C	MPa	2,500	-
Tensile Strength	DIN EN ISO 527	5 mm/min 23 °C	MPa	43	-
Elongation at Break	DIN EN ISO 527	5 mm/min 23 °C	%	> 30	-
Flexural Modulus	DIN EN ISO 178	2 mm/min 23 °C	MPa	2,550	-
Flexural Strength	DIN EN ISO 178	2 mm/min 23 °C	MPa	66	-
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm 23 °C	kJ/m <sup>2</sup>	10	-
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm -30 °C	kJ/m <sup>2</sup>	5	-
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm 23 °C	kJ/m <sup>2</sup>	45	-
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm -30 °C	kJ/m <sup>2</sup>	40	-

PHYSICAL.....					
Density	DIN EN ISO 1183	23 °C, 50 % r.h.	g/cm <sup>3</sup>	1.12	-
Moisture Absorption (equilibrium)	DIN EN ISO 62	23 °C, 50 % r.h.	%	-	-

THERMAL.....					
Heat deflection temperature (HDT/A)	DIN EN ISO 75-1	1,8 MPa	°C	65	-
Vicat Softening Temperature (B 50)	DIN EN ISO 306	50 N, 50 °C/h	°C	126	-
Melt Mass-Flow Rate (MFR)	DIN EN ISO 1133	260 °C, 5 kg	g/10 min	16	-
Processing Shrinkage	DIN EN ISO 294-4	23 °C	%	0.3 - 0.7	-
Flammability (own test)	UL94	1.5 mm	--	HB	-