

TECHNICAL DATA SHEET

ROMILOY[®] 4010/07-1 UV

ROMIRA

PA/ABS, injection moulding grade, easy demolding, UV stabilized

PROPERTY	Test Method	Condition	Unit	Value*	
----------	-------------	-----------	------	--------	--

MECHANICAL.....				Dry as molded	conditioned
Tensile Modulus	DIN EN ISO 527	1 mm/min 23 °C	MPa	2,000	-
Tensile Strength	DIN EN ISO 527	50 mm/min 23 °C	MPa	43	-
Elongation at Break	DIN EN ISO 527	50 mm/min 23 °C	%	> 50	-
Flexural Modulus	DIN EN ISO 178	2 mm/min 23 °C	MPa	1,700	-
Flexural Strength	DIN EN ISO 178	2 mm/min 23 °C	MPa	66	-
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm 23 °C	kJ/m ²	62	-
Notched Impact Strength (Charpy)	DIN EN ISO 179/1eA	80 x 10 x 4 mm -30 °C	kJ/m ²	19	-
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm 23 °C	kJ/m ²	n.b.	-
Impact Strength (Charpy)	DIN EN ISO 179/1eU	80 x 10 x 4 mm -30 °C	kJ/m ²	n.b.	-

PHYSICAL.....					
Density	DIN EN ISO 1183	23 °C, 50 % r.h.	g/cm ³	1.06	-
Moisture Absorption (equilibrium)	DIN EN ISO 62	23 °C, 50 % r.h.	%	-	-

THERMAL.....					
Heat deflection temperature (HDT/B)	DIN EN ISO 75-1	0,45 MPa	°C	96	-
Vicat Softening Temperature (B 50)	DIN EN ISO 306	50 N, 50 °C/h	°C	114	-
Melt Mass-Flow Rate (MFR)	DIN EN ISO 1133	260 °C, 5 kg	g/10 min	32	-
Thermal Coefficient of Linear Expansion	ISO 11359-2	20 °C - 80 °C	10 ⁻⁴ · K ⁻¹	1.4	-
Processing Shrinkage	DIN EN ISO 294-4	23 °C	%	0.6 - 0.9	-
Flammability (own test)	UL94	1.5 mm	--	HB	-

ROMIRA GMBH