

# Technical Data Sheet

## ROMILOY® 8170



ABS / PC-Blend, flame retardant, free of antimony, chlorine and bromine

Properties	Unit	Test Method	Test Condition	Value*	Remarks
<b>Mechanical.....</b>					
Tensile Modulus	MPa	ISO 527	23°C 1 mm/min	2,600	
Tensile Strength	MPa	ISO 527	23°C 50 mm/min	63	
Elongation at Break	%	ISO 527	23°C 50 mm/min	30	
Flexural Modulus	MPa	ISO 178	23°C 2 mm/min	2,600	
Flexural Strength	MPa	ISO 178	23°C 2 mm/min	98	
Impact Strength Notched (Charpy)	kJ/m²	ISO 179 1eA	80 x 10 x 4 mm 23°C	25	
Impact Strength (Charpy)	kJ/m²	ISO 179 1eU	80 x 10 x 4 mm 23°C	n.b.	
<b>Physical.....</b>					
Density	g/cm³	ISO 1183	23°C, 50% RH	1.17	
<b>Thermal.....</b>					
Heat Distortion Temperature (HDT A)	°C	ISO 75	1.8 MPa	76	
Vicat Softening Temperature (B 50)	°C	ISO 306	50°C/h 50 N	105	
Melt Flow Rate MFR	g/10 min	ISO 1133	240°C, 5 kg 260°C, 5 kg	25 40	
Glow Wire Test (GWFI)	°C	IEC 60695-2-12	3.0 mm	850	
Moulding Shrinkage	%	ISO 294-4	23°C	0.4 - 0.7	
Flammability	Class	UL 94	1.5 mm	V-0	UL listed

\* = Average figures which could vary with each production batch due to addition of pigments, antistatic agents, slip agents, light stabilizers or other additives.

**ROMIRA GMBH**