

VAMPGREEN H 00U 09 SF V0 28 05 E

PE resin from sustainable feedstock, unfilled, flame retarded
halogen free, dissipative, for extrusion



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,16
MVR (230°C/2,16 kg)	-	ISO-1133	cm ³ /10 min	1,5
Linear Mould Shrinkage	-	ASTM D-955	%	2,5
Trasversal Mould Shrinkage	-	ASTM D-955	%	2,5
Water Adsorption	23°C-24h	ASTM D-570	%	0,02
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	75
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	40
Long Term Temperature	-	Internal Method	°C	65
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	4
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	25
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	15
Elongation at Break	23 °C	ISO-527/1-2	%	>10
Tensile Modulus	23 °C	ISO-527/1-2	MPa	1500
ELECTRICAL PROPERTIES				
Surface Resistivity	-	ASTM D257	Ohm	10 ^{^9}

VAMPGREEN H 00U 09 SF V0 28 05 E

PE resin from sustainable feedstock, unfilled, flame retarded
halogen free, dissipative, for extrusion



FLAME RESISTANCE

Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
Oxygen Index (LOI)	-	ISO-4589-1/-2	%	35