

# VAMPGREEN N 00U RC V0 26 1S 06

PA6 post industrial recycled based injection moulding compound, unfilled, flame retarded halogen free



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,38
Linear Mould Shrinkage	-	ASTM D-955	%	1,6
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,6
Water Adsorption	23°C-24h	ASTM D-570	%	1,5
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	180
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	65
Ball Pressure Test	-	IEC 60695-10-2	°C	180
Long Term Temperature	-	Internal Method	°C	120
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	7,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	NB
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	40
Elongation at Break	23 °C	ISO-527/1-2	%	>20
Tensile Modulus	23 °C	ISO-527/1-2	MPa	2700
<b>ELECTRICAL PROPERTIES</b>				
Comparative Tracking Index	-	IEC 60112	V	250

# VAMPGREEN N 00U RC V0 26 1S 06

PA6 post industrial recycled based injection moulding compound, unfilled, flame retarded halogen free



FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
Thickness 0,8 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775