VAMPGREEN N 30G RC V2 28 1S 05 MF

PA6 post industrial recycled based injection moulding compound, 30% glass fiber reinforced, flame retarded halogen free

PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm^3	1,43
Linear Mould Shrinkage	-	ASTM D-955	%	0,9
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,8
Water Adsorption	23°C-24h	ASTM D-570	%	1,2
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	205
Long Term Temperature	-	Internal Method	°C	120
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m^2	3,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m^2	30
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	70
Elongation at Break	23 °C	ISO-527/1-2	%	2,5
Tensile Modulus	23 °C	ISO-527/1-2	MPa	6500
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600

VAMPGREEN N 30G RC V2 28 1S 05 MF

PA6 post industrial recycled based injection moulding compound, 30% glass fiber reinforced, flame retarded halogen free

FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V2
Thickness 1,6 mm	-	UL 94	-	V2
Thickness 0,8 mm	-	UL 94	-	V2
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960