

VAMPGREEN P 10M RC V2 26 1S 07 C NF

PP post industrial recycled based injection moulding compound, 10% mineral filled, flame retarded with halogen.



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,01
MVR (230°C/2,16 kg)	-	ISO-1133	cm ³ /10 min	30
Linear Mould Shrinkage	-	ASTM D-955	%	1,8
Trasversal Mould Shrinkage	-	ASTM D-955	%	1,8
Water Adsorption	23°C-24h	ASTM D-570	%	0,02
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	85
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	55
Ball Pressure Test	-	IEC 60695-10-2	°C	75
Long Term Temperature	-	Internal Method	°C	75
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	3,5
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	40
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	25
Elongation at Break	23 °C	ISO-527/1-2	%	>10
Tensile Modulus	23 °C	ISO-527/1-2	MPa	1600
ELECTRICAL PROPERTIES				
Comparative Tracking Index	-	IEC 60112	V	600

VAMPGREEN P 10M RC V2 26 1S 07 C NF

PP post industrial recycled based injection moulding compound, 10% mineral filled, flame retarded with halogen.



FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V2
Thickness 1,6 mm	-	UL 94	-	V2
Thickness 0,8 mm	-	UL 94	-	V2
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	675
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	675