

# VAMPLEN 3026 V0 CB DF

PP resin, 30% glass fiber reinforced, flame retarded with halogens for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,46
MVR (230°C/2,16 kg)	-	ISO-1133	cm <sup>3</sup> /10 min	3,5
Linear Mould Shrinkage	-	ASTM D-955	%	0,3
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,7
Water Adsorption	23°C-24h	ASTM D-570	%	0,02
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	130
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	140
Long Term Temperature	-	Internal Method	°C	120
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	7
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	25
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	65
Elongation at Break	23 °C	ISO-527/1-2	%	2
Tensile Modulus	23 °C	ISO-527/1-2	MPa	8000
<b>ELECTRICAL PROPERTIES</b>				
Comparative Tracking Index	-	IEC 60112	V	600

# VAMPLEN 3026 V0 CB DF

PP resin, 30% glass fiber reinforced, flame retarded with halogens for injection moulding



## FLAME RESISTANCE

Thickness 3,0 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
Thickness 0,8 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	850
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	850