

VAMPLUB C 00U 4TF

PC resin unfilled with improved slip properties for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,30
MVR (300°C/1,2 kg)	-	ISO-1133	cm ³ /10 min	15
Linear Mould Shrinkage	-	ASTM D-955	%	0,7
Trasversal Mould Shrinkage	-	ASTM D-955	%	0,7
Water Adsorption	23°C-24h	ASTM D-570	%	0,15
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	145
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	130
Long Term Temperature	-	Internal Method	°C	135
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	8
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	100
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	45
Elongation at Break	23 °C	ISO-527/1-2	%	>10
Tensile Modulus	23 °C	ISO-527/1-2	MPa	2000
FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V2
Thickness 1,6 mm	-	UL 94	-	V2

VAMPLUB C 00U 4TF

PC resin unfilled with improved slip properties for injection moulding



TRIBOLOGICAL PROPERTIES

Wear Factor K	-	Thrust Washer	-	70
Coeff. of Friction	Dynamic	ASTM D-1894	-	0,14
Coeff. of Friction	Static	ASTM D-1894	-	0,18