

# VAMPORAN 0024 V0 13

PPOm resin unfilled, flame retarded halogen free for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
<b>PHYSICAL PROPERTIES</b>				
Density	-	ISO-1183	g/cm <sup>3</sup>	1,12
MVR (280°C/5 kg)	-	ISO-1133	cm <sup>3</sup> /10 min	20
Water Adsorption	23°C-24h	ASTM D-570	%	0,07
<b>THERMAL PROPERTIES</b>				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	130
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	115
Long Term Temperature	-	Internal Method	°C	100
<b>MECHANICAL PROPERTIES</b>				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m <sup>2</sup>	6
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m <sup>2</sup>	45
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	50
Elongation at Break	23 °C	ISO-527/1-2	%	9
Tensile Modulus	23 °C	ISO-527/1-2	MPa	2700
<b>ELECTRICAL PROPERTIES</b>				
Comparative Tracking Index	-	IEC 60112	V	300

# VAMPORAN 0024 V0 13

PP0m resin unfilled, flame retarded halogen free for injection moulding



## FLAME RESISTANCE

Thickness 3,2 mm	-	UL 94	-	V0
Thickness 1,6 mm	-	UL 94	-	V0
GWFI (1 mm)	-	IEC 60695-2-12	°C / mm	960
GWFI (2 mm)	-	IEC 60695-2-12	°C / mm	960
GWIT (1 mm)	-	IEC 60695-2-13	°C / mm	775
GWIT (2 mm)	-	IEC 60695-2-13	°C / mm	775