

VAMPORAN 2028 V1

PPOm resin, 20% glass fiber reinforced, flame retarded
halogen free for injection moulding



PROPERTY	CONDITIONS	NORMS	UNITS	VALUE
PHYSICAL PROPERTIES				
Density	-	ISO-1183	g/cm ³	1,29
MVR (280°C/5 kg)	-	ISO-1133	cm ³ /10 min	20
Linear Mould Shrinkage	-	ASTM D-955	%	0,2
Water Adsorption	23°C-24h	ASTM D-570	%	0,22
THERMAL PROPERTIES				
Vicat Softening Point	VICAT B (50 N)	ASTM D-1525	°C	110
Heat Distortion Temperature	HDT A (1,80 MPa)	ASTM D-648	°C	100
Long Term Temperature	-	Internal Method	°C	100
MECHANICAL PROPERTIES				
Impact Strength Izod Notched	23 °C	ISO-180/A	kJ/m ²	7
Impact Strength Izod Unnotched	23 °C	ISO-180/U	kJ/m ²	30
Tensile Strength at Break	23 °C	ISO-527/1-2	MPa	80
Elongation at Break	23 °C	ISO-527/1-2	%	2,2
Tensile Modulus	23 °C	ISO-527/1-2	MPa	6000
FLAME RESISTANCE				
Thickness 3,2 mm	-	UL 94	-	V1
Thickness 1,5 mm	-	UL 94	-	V1