

VECTOR 4213A / VECTOR 4213N Styrene-Isoprene-Styrene / Styrene-Isoprene (SIS/SI) Block Copolymer Blends

- Blend of linear SIS ⁽¹⁾ triblock and SI ⁽¹⁾ diblock copolymer.
- Contains ~25% SI diblock copolymer.
- Medium styrene.

VECTOR 4213A and VECTOR 4213N styrenic block copolymers are blended products composed of a linear SIS triblock copolymer and an SI diblock copolymer. They are well-suited for use in hot melt adhesives for hygiene applications requiring superior cohesive strength and heat resistance along with low creep compliance.

- VECTOR 4213A SIS/SI is offered as a dense pellet supplied from the United States.
- VECTOR 4213N SIS/SI is offered as a porous pellet supplied from China.

Polymer Properties	Test Method	Units	Typical Value ⁽²⁾
Styrene	TSRC / Dexco Method	wt%	25
Diblock Content	TSRC / Dexco Method	wt%	25
Melt Flow Rate (200°C/5kg)	ASTM D1238	g/10 min	12
Solution Viscosity ⁽³⁾	ASTM D2196	cps	370
Ash	ASTM D5630	wt%	0.3
Physical Properties			
Tensile Strength ⁽⁴⁾	TSRC / Dexco Method	MPa	15
300% Modulus ⁽⁴⁾	TSRC / Dexco Method	MPa	2.9
Elongation ⁽⁴⁾	TSRC / Dexco Method	%	1100
Hardness ⁽⁵⁾	ASTM D2240	Shore A	51
Bulk Density	ASTM D1895	g/cm ³	0.55 (4213A) 0.33 (4213N)
Specific Gravity	ASTM D792		0.94

1) SIS denotes a linear styrene-isoprene-styrene triblock copolymer; SI denotes a styrene-isoprene diblock copolymer.

2) Not to be construed as specifications.

3) 25 wt% in Toluene; 25°C.

4) Roll-milled, compression-molded plaques.

5) Dwell time - 1 second.