



台橡 (南通) 实业有限公司
TSRC (Nantong) Industrial Ltd.

Vector 4213N

POLYMER DATA

Vector 4213N

- Polymerization System -- Solution Polymerization, styrene -isoprene block copolymer.
- Stabilizer -- Non-staining
- Characteristics -- Medium molecular weight
-- Excellent hot stability
-- High strength
-- Easy processing
-- Medium melt viscosity
-- Good solubility in common adhesive solvent
- Application -- Mainly for adhesives (HMA, PSA); plastic modification; asphalt modification

Specification Range

<u>Polymer Properties</u>		<u>min</u>	<u>max</u>	<u>Test Method</u>
Melt Flow Rate, @200°C/5kg	(dg/min)	8.5	15.5	ASTM D-1238
Ash (including AB*)	(% wt)	0.43	0.73	ASTM D-5667
Styrene	(% wt)	23.0	27.0	TDM-01
Total Volatiles	(% wt)	—	0.5	TDM-03
Diblock	(% wt)	22.5	27.5	TDM-07

* AB : Antiblocking Agent