



TRIVALENCE

TriVET™ 12G30FR5 (U,R)

Polybutylene Terephthalate

General Information

Product Description

Glass fiber reinforced PBT, flame retardant

FEATURES

- 30% Glass Fiber Reinforced
- Chemical Resistance
- RoHS/REACH Compliant
- Medium Flow

-Flame Retardant

ADDITIONAL FORMULAS

- Added Release "R"
- Added UV "U"

COLOR

-All

General

- Typical Applications** -Appliance, electrical, lawn & garden, recreation
- Processing Method** -Injection/Extrusion
- Form(s)** -Pellets
- Availability** -North America, Europe, Latin America

ASTM / ISO Properties¹

Physical

	Nominal Value	Unit	Test Method
Density	1.65	g/cm ³	ASTM D792
Melt Flow Rate (250°C/2.16kg)	16	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.3 to 0.5	%	ASTM D955
Outdoor Suitability - QUV ("U" grades only)	Pass		QUV - TVT Internal

Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength, yld	19,200	psi	ASTM D638
Tensile Elongation	>2	%	ASTM D638
Flexural Modulus	1450000	psi	ASTM D790
Notched Izod Impact, 73F	1.8	ft-lb/in	ASTM D256

Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa)(0.25in)	425	°F	ASTM D648
Deflection Temperature Under Load (1.8 MPa)(0.25in)	408	°F	ASTM D648
CLTE - Flow	1.4E-5	in/in/°F	ASTM E831

Flammability

	Nominal Value	Unit	Test Method
0.06 in	V0	Bum Rate	UL94 TVT Internal
0.125 in	5V	Bum Rate	UL94 TVT Internal

Recommended Processing Guidance

Drying Temperature	220 to 255	°F
Drying Time	3 to 6	Hours
Suggested Max Moisture	0.02	%
Processing Melt Temperature	450 to 490	°F
Mold Temperature	140 to 190	°F