



**TRIVALENCE**

# TriVOL 21G10(U,R)

**Polypropylene**

**General Information**

**Product Description**

Polypropylene, homopolymer, glass filled.

**FEATURES**

- High Flow
- Homopolymer
- 10% Glass Reinforced
- Good Structural Strength

**ADDITIONAL FORMULAS**

- RoHS/REACH Compliant
- Added Release "R"
- Added UV "U"

**COLOR**

- All

**General**

**Typical Applications**

-Appliance, electrical, lawn & garden, automotive, packaging, industrial

**Processing Method**

-Injection/Extrusion

**Form(s)**

-Pellets

**Availability**

-North America, Europe, Asia, Latin America

**ASTM / ISO Properties<sup>1</sup>**

**Physical**

	Nominal Value	Unit	Test Method
Density	0.98	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (230°C/2.16kg)	18	g/10min	ASTM D1238
Molding Shrinkage - Flow (3.2mm)	0.5 to 0.7	%	TVT Internal
Outdoor Suitability (QUV) ("U" grades)	Pass		TVT Internal

**Mechanical**

	Nominal Value	Unit	Test Method
Tensile Strength, yld	6,800	psi	ASTM D638
Flexural Modulus	300,000	psi	ASTM D790
Notched Izod Impact	0.8	ft-lbs/in	ASTM D256

**Thermal**

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa)	250	°F	ASTM D648

**Flammability**

	Nominal Value	Unit	Test Method
0.06 in	HB		UL94 TVT Internal

**Recommended Processing Guidance**

	Nominal Value	Unit
Drying Temperature	140-180	°F
Drying Time	1 to 3	Hours
Suggested Max Moisture	0.05	%
Processing Melt Temperature	420 to 480	°F
Mold Temperature	80 to 140	°F