

Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN

Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

Zytel® RS LCPA resins contain between 20% and 100% renewably sourced material (by weight) derived from castor beans.

Zytel® RS LC3090 NC010 is a renewable sourced polyamide 610 containing a minimum of 60% renewably sourced ingredient by weight. It is an unreinforced, high viscosity grade, developed for extrusion applications.

Product information

Resin Identification	PA610	ISO 1043
Part Marking Code	>PA610<	ISO 11469
ISO designation	ISO 16396-PA610,,M1G1N,S18-020	

Rheological properties

	dry/cond.		
Viscosity number	170 ^[1] /*	cm ³ /g	ISO 307, 1628
Intrinsic viscosity	1.55		ISO 307, 1628
Moulding shrinkage, parallel	1.2 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.2 / -	%	ISO 294-4, 2577

[1]: Sulfuric acid 96%

Typical mechanical properties

	dry/cond.		
Tensile modulus	2300 / 1200	MPa	ISO 527-1/-2
Flexural modulus	1900 / -	MPa	ISO 178
Flexural strength	86 / -	MPa	ISO 178
Charpy impact strength, 23°C	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.6 / -	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.39 / 0.44		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	60 / 50	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	54 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	151 / *	°C	ISO 75-1/-2

Flammability

FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80 mm/min	ISO 3795 (FMVSS 302)

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.4 / *	%	Sim. to ISO 62
Water absorption, 2mm	3.3 / *	%	Sim. to ISO 62
Water absorption, Immersion 24h	0.58 / *	%	Sim. to ISO 62
Density	1080 / -	kg/m ³	ISO 1183

Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN

Extrusion

Drying Temperature	75 - 80 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.06 %
Melt Temperature Optimum	245 °C
Melt Temperature Range	240 - 255 °C


Characteristics

Processing	Injection Moulding, Extrusion, Other Extrusion
Delivery form	Pellets
Sustainability	Bio-Content

Dynamic Tensile modulus-temperature (dry)

Zytel® RS LC3090 NC010


LONG CHAIN POLYAMIDE RESIN



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN


Dynamic Tensile modulus-temperature (cond.)



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN


Stress-strain (dry)



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN


Stress-strain (cond.)



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN


Secant modulus-strain (dry)



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN


Secant modulus-strain (cond.)



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN


Tensile modulus-temperature (dry)



Zytel® RS LC3090 NC010

LONG CHAIN POLYAMIDE RESIN

Tensile modulus-temperature (cond.)



Printed: 2025-05-29

Page: 10 of 10

Revised: 2025-04-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.