

Zytel® LC7601 BK010 (PRELIMINARY)

LONG CHAIN POLYAMIDE RESIN

Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

Zytel® LC7601 BK010 is a flexible, toughened, plasticized black polyamide resin for extrusion. It has low moisture absorption, excellent chemical resistance and good heat resistance.

Product information

Resin Identification	PA-IP	ISO 1043
Part Marking Code	>PA-IP<	ISO 11469
ISO designation	ISO 16396-PA-IP,,ECG1H,S10-005	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	2.1 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.3 / -	%	ISO 294-4, 2577
Melt viscosity, @ 1000 sec-1, 250 °C	150 / *	Pa.s	ISO 11443

Typical mechanical properties

	dry/cond.		
Tensile modulus	500 / -	MPa	ISO 527-1/-2
Flexural modulus	500 / -	MPa	ISO 178
Charpy impact strength, 23 °C	N / -	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30 °C	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	115 / - ^[P]	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40 °C	13 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	92 / -	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40 °C	13.0 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.47 / -		

[P]: Partial Break

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	209 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10 °C/min	50 / 40	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	43 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	69 / *	°C	ISO 75-1/-2
Thermal conductivity of melt	0.17 ^[DS]	W/(m K)	ISO 22007-2
Specific heat capacity of melt	2700 ^[DS]	J/(kg K)	ISO 22007-4

[DS]: Derived from similar grade

Flammability

FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80 mm/min	ISO 3795 (FMVSS 302)

Zytel® LC7601 BK010 (PRELIMINARY)

LONG CHAIN POLYAMIDE RESIN

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	0.8 / *	%	Sim. to ISO 62
Density	1030 / -	kg/m ³	ISO 1183

Extrusion

Drying Temperature	75 - 80 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.06 %
Melt Temperature Optimum	225 °C
Melt Temperature Range	220 - 230 °C

Characteristics

Processing	Film Extrusion, Extrusion, Sheet Extrusion, Other Extrusion, Coatable, Casting
Delivery form	Pellets
Additives	Plasticiser
Special characteristics	High impact or impact modified, Light stabilised or stable to light, Heat stabilised or stable to heat

Automotive


OEM
Renault-Nissan

ADDITIONAL INFORMATION
UB16c, No Spec, Special Part Approval, See
Your CE Account Manager.

Zytel® LC7601 BK010 (PRELIMINARY)

LONG CHAIN POLYAMIDE RESIN


Viscosity-shear rate



Zytel® LC7601 BK010 (PRELIMINARY)

LONG CHAIN POLYAMIDE RESIN

Shearstress-shear rate



Printed: 2025-05-29

Page: 4 of 4

Revised: 2025-04-23 Source: Celanese Materials Database

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.