

Zytel® 103FHS BKB009

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 103FHS BKB009 is a heat stabilised, internally lubricated polyamide 66 resin for injection moulding. It was developed for fast cycles and high productivity.

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
ISO designation	ISO 16396-PA66,,M1CG1HR,S14-030	

Rheological properties

	dry/cond.		
Viscosity number	150 ^[1] /*	cm ³ /g	ISO 307, 1628
Moulding shrinkage, parallel	1.3 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.3 / -	%	ISO 294-4, 2577
[1]: Sulfuric acid 96%			

Typical mechanical properties

	dry/cond.		
Tensile modulus	3100 / -	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	85 / -	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	4.3 / -	%	ISO 527-1/-2
Nominal strain at break	15 / -	%	ISO 527-1/-2
Flexural modulus	2800 / -	MPa	ISO 178
Charpy impact strength, 23°C	250 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5 / -	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	5 / -	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	5.0 / -	kJ/m ²	ISO 180/1A
Izod impact strength, 23°C	200 / -	kJ/m ²	ISO 180/1U
Poisson's ratio	0.37 / -		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	65 / 40	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	64 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	195 / *	°C	ISO 75-1/-2
RTI, electrical, 0.75mm	140	°C	UL 746B
RTI, electrical, 1.5mm	140	°C	UL 746B

Zytel® 103FHS BKB009

NYLON RESIN

RTI, electrical, 3.0mm	140	°C	UL 746B
RTI, impact, 0.75mm	95	°C	UL 746B
RTI, impact, 1.5mm	110	°C	UL 746B
RTI, impact, 3.0mm	110	°C	UL 746B
RTI, strength, 0.75mm	115	°C	UL 746B
RTI, strength, 1.5mm	125/*	°C	UL 746B
RTI, strength, 3.0mm	125	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-2/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-2/*	class	IEC 60695-11-10
Thickness tested	0.71/*	mm	IEC 60695-11-10
UL recognition	yes/*		UL 94
Oxygen index	28/*[DS]	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.75mm	850/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	725/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	725/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3.0mm	725/-	°C	IEC 60695-2-13
FMVSS Class	DNI		ISO 3795 (FMVSS 302)

[DS]: Derived from similar grade

Physical/Other properties

	dry/cond.		
Density	1140/-	kg/m ³	ISO 1183

VDA Properties

	dry/cond.		
Emission of organic compounds	1.2	µgC/g	VDA 277
Odour	2.5	class	VDA 270
Fogging, F-value (refraction)	70/*	%	ISO 6452
Fogging, G-value (condensate)	0.3/*	mg	ISO 6452

Injection

Drying Recommended	yes	
Drying Temperature	80	°C
Drying Time, Dehumidified Dryer	2 - 4	h
Processing Moisture Content	≤0.2	%
Melt Temperature Optimum	290	°C
Min. melt temperature	280	°C
Max. melt temperature	300	°C
Screw tangential speed	≤0.4	m/s
Mold Temperature Optimum	70	°C
Min. mould temperature	50	°C
Max. mould temperature	90	°C
Hold pressure range	50 - 100	MPa
Hold pressure time	4	s/mm

Zytel® 103FHS BKB009

NYLON RESIN

Ejection temperature

190 °C

Characteristics

Processing

Injection Moulding

Special characteristics

Heat stabilised or stable to heat

Automotive

OEM

STANDARD

ADDITIONAL INFORMATION

Geely

Q/JL J124010-2019

General Motors

GMW16036P-PA66

Black

Stellantis - Chrysler

MS.50017 / CPN-1899

Black

VW Group

VW 50127 PA66-1


VW Group

VW 50133 PA66-1-A

Zytel® 103FHS BKB009

NYLON RESIN


Viscosity-shear rate
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN


Shearstress-shear rate
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN


Stress-strain (dry)
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN


Stress-strain (cond.)
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN


Secant modulus-strain (dry)
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN


Secant modulus-strain (cond.)
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN

Tensile modulus-temperature (dry)
(measured on Zytel® 103FHS NC010)



Zytel® 103FHS BKB009

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C

Zytel® 103FHS BKB009

NYLON RESIN

- ✓ Sodium Carbonate solution (20% by mass), 23 °C
- ✓ Sodium Carbonate solution (2% by mass), 23 °C
- ✗ Zinc Chloride solution (50% by mass), 23 °C

Other

- ✓ Ethyl Acetate, 23 °C
- ✗ Hydrogen peroxide, 23 °C
- ✗ DOT No. 4 Brake fluid, 130 °C
- ✗ Ethylene Glycol (50% by mass) in water, 108 °C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23 °C
- ✓ 50% Oleic acid + 50% Olive Oil, 23 °C
- ✓ Water, 23 °C
- ✗ Water, 90 °C
- ✗ Phenol solution (5% by mass), 23 °C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).