

CELANEX® 3309HRT

30% glass-fiber reinforced; hydrolysis resistant; toughened PBT grade; not lubricated

Celanex 3309HRT is a non-lubricated, 30% fiberglass reinforced Polybutylene Terephthalate that has excellent hydrolysis resistance, toughness and improved flow.

Product information

Part Marking Code

PBT-I-GF30

ISO 11469

Rheological properties

Melt mass-flow rate

22 g/10min

ISO 1133

Melt mass-flow rate, Temperature

250 °C

Melt mass-flow rate, Load

2.16 kg

Moulding shrinkage range, parallel

0.1 - 0.5 %

ISO 294-4, 2577

Moulding shrinkage range, normal

0.5 - 0.9 %

ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus

8700 MPa

ISO 527-1/-2

Stress at break, 5mm/min

115 MPa

ISO 527-1/-2

Strain at break, 5mm/min

2.8 %

ISO 527-1/-2

Flexural Modulus

8700 MPa

ISO 178

Flexural Strength

190 MPa

ISO 178

Charpy impact strength, 23°C

53 kJ/m²

ISO 179/1eU

Charpy impact strength, -30°C

38 kJ/m²

ISO 179/1eU

Charpy notched impact strength, 23°C

10 kJ/m²

ISO 179/1eA

Charpy notched impact strength, -30°C

10 kJ/m²

ISO 179/1eA

Izod notched impact strength, 23°C

10 kJ/m²

ISO 180/1A

Izod impact strength, 23°C

49 kJ/m²

ISO 180/1U

Izod impact strength, -30°C

32 kJ/m²

ISO 180/1U

Shore D hardness, 15s

82

ISO 48-4 / ISO 868

Thermal properties

Melting temperature, 10°C/min

225 °C

ISO 11357-1/-3

Temp. of deflection under load, 1.8 MPa

208 °C

ISO 75-1/-2

Temp. of deflection under load, 0.45 MPa

222 °C

ISO 75-1/-2

Coeff. of linear therm. expansion, parallel

20 E-6/K

ISO 11359-1/-2

Coeff. of linear therm. expansion, normal

90 E-6/K

ISO 11359-1/-2

Electrical properties

Relative permittivity, 100Hz

2.8

IEC 62631-2-1

Relative permittivity, 1MHz

2.8

IEC 62631-2-1

Dissipation factor, 1MHz

110 E-4

IEC 62631-2-1

Volume resistivity

1E15 Ohm.m

IEC 62631-3-1

Surface resistivity

2E17 Ohm

IEC 62631-3-2

Electric strength

38 kV/mm

IEC 60243-1

CELANEX® 3309HRT

Comparative tracking index

PLC 1 PLC

UL 746A

Other properties

Humidity absorption, 2mm

0.15 %

Sim. to ISO 62

Density

1500 kg/m³

ISO 1183

Injection

Drying Temperature

120 - 130 °C

Drying Time, Dehumidified Dryer

4 h

Processing Moisture Content

0.02 %

Max. mould temperature

65 - 93 °C

Injection speed

medium-fast

Additional information

Injection molding

Rear Temperature 450-470(230-240) deg F (deg C)

Center Temperature 460-480(235-250) deg F (deg C)

Front Temperature 470-500(240-260) deg F (deg C)

Nozzle Temperature 480-500(250-260) deg F (deg C)

Melt Temperature 460-500(235-260) deg F (deg C)

Mold Temperature 150-200(65-93) deg F (deg C)

Back Pressure 0-50 psi

Screw Speed Medium

Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Texts

Pre-drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

Injection molding

Rear Temperature 450-470(230-240) deg F (deg C)

Center Temperature 460-480(235-250) deg F (deg C)

Front Temperature 470-500(240-260) deg F (deg C)

Nozzle Temperature 480-500(250-260) deg F (deg C)

Melt Temperature 460-500(235-260) deg F (deg C)

Mold Temperature 150-200(65-93) deg F (deg C)

CELANEX® 3309HRT

Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Injection molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours.

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Stellantis - Chrysler	CPN 4615	CANOD