

CELANEX® 3316HR

CELANEX® PBT

Celanex 3316HR is a flame retarded, hydrolysis resistant, 30% fiberglass reinforced polybutylene terephthalate which has an excellent balance of mechanical properties and processability.

Product information

Resin Identification	PBT-I-GF30 FR(17)	ISO 1043
Part Marking Code	>PBT-I-GF30 FR(17)<	ISO 11469

Rheological properties

Melt mass-flow rate	6 g/10min	ISO 1133
Melt mass-flow rate, Temperature	250 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage range, parallel	0.3 - 0.5 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.8 - 1.1 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	9850 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	115 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.5 %	ISO 527-1/-2
Flexural modulus	8950 MPa	ISO 178
Flexural strength	180 MPa	ISO 178
Charpy notched impact strength, 23 °C	8.5 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10 °C/min	225 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	202 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	25 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	90 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
Thickness tested	0.75 mm	IEC 60695-11-10
Burning Behav. 5V at thickness h	5VA class	IEC 60695-11-20
Thickness tested	1.5 mm	IEC 60695-11-20
UL recognition	yes	UL 94
Glow Wire Flammability Index, 3.0mm	960 °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 3.0mm	750 °C	IEC 60695-2-13
FMVSS Class	DNI	ISO 3795 (FMVSS 302)

Electrical properties

Relative permittivity, 1MHz	2.9	IEC 62631-2-1
Dissipation factor, 1MHz	145 E-4	IEC 62631-2-1
Volume resistivity	>1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15 Ohm	IEC 62631-3-2
Comparative tracking index	250	IEC 60112

CELANEX® 3316HR

CELANEX® PBT

Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, Immersion 24h	0.05 %	Sim. to ISO 62
Density	1640 kg/m ³	ISO 1183

VDA Properties

Emission of organic compounds	15 µgC/g	VDA 277
-------------------------------	----------	---------

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	250 °C
Min. melt temperature	240 °C
Max. melt temperature	260 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	130 °C
Ejection temperature	191 °C

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent, Flame retardant
Special characteristics	Flame retardant, Hydrolysis resistant

Additional information

Processing Notes

Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

Storage

For subsequent storage of the material in the dryer until processed (≤ 60 h) it is necessary to lower the temperature to 100° C.


CELANEX® 3316HR

CELANEX® PBT

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Li Auto	Q/LiA5310038	2021 (V2)
Renault	UB22c, No Spec, Special Part Approval, See Your CE Account Manager.	
Renault	UB22d, No Spec, Special Part Approval, See Your CE Account Manager.	
Renault	UB22e, No Spec, Special Part Approval, See Your CE Account Manager.	
Stellantis	B62 0300 / 61/219E/215M/C4	01378_20_00624


Viscosity-shear rate



CELANEX® 3316HR

CELANEX® PBT


Shearstress-shear rate



CELANEX® 3316HR

CELANEX® PBT


Stress-strain



CELANEX® 3316HR

CELANEX® PBT

Secant modulus-strain



Printed: 2025-05-30

Page: 6 of 6

Revised: 2025-05-16 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.