

CELANEX® 6407

CELANEX® PBT

Celanex 6407 is a 30% glass/mineral reinforced resin particularly suited for large exterior automotive components, where extended flow, flatness and good surface appearance is essential.

Product information

Resin Identification	(PBT-I+PET)-GF30	ISO 1043
Part Marking Code	>(PBT-I+PET)-GF30<	ISO 11469

Rheological properties

Melt mass-flow rate	21 g/10min	ISO 1133
Melt mass-flow rate, Temperature	265 °C	
Melt mass-flow rate, Load	2.16 kg	
Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	8000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	85 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.1 %	ISO 527-1/-2
Flexural modulus	8000 MPa	ISO 178
Flexural strength	140 MPa	ISO 178
Charpy notched impact strength, 23 °C	6 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	6.2 kJ/m ²	ISO 180/1A
Poisson's ratio	0.34 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	172 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	209 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	19 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	70 E-6/K	ISO 11359-1/-2

Physical/Other properties

Water absorption, 2mm	0.1 %	Sim. to ISO 62
Water absorption, Immersion 24h	0.1 %	Sim. to ISO 62
Density	1520 kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	265 °C
Min. melt temperature	255 °C
Max. melt temperature	275 °C
Screw tangential speed	0.1 - 0.3 m/s
Mold Temperature Optimum	100 °C

CELANEX® 6407

CELANEX® PBT

Min. mould temperature 90 °C
Max. mould temperature 130 °C

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Special characteristics	High Gloss, Low Warpage

Additional information

Processing Notes

Pre-Drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250 °F (121 °C) for 4 hours.

Storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
General Motors	GMW17448P-PBT+PET-GF15M15	
Stellantis - Chrysler	MS.50103 / CPN-3669	Black