

CELANEX® XFR 6842 GF30 HRCT (PRELIMINARY)

Halogen-free, nom. 30% glass-fiber reinforced, flame retardant grade with improved hydrolysis resistance and high CTI
Celanex XFR 6842 GF30 HRCT is a halogen and antimony free flame retardant glass fiber reinforced PBT grade with good processability and excellent hydrolysis resistance. It is suitable for parts requiring enhanced electrical tracking resistance (CTI 600V), toughness, and flame retardancy. The product is WEEE and RoHS compliant.

Rheological properties

Melt volume-flow rate	8 cm ³ /10min	ISO 1133
Temperature	250 °C	
Load	5 kg	

Typical mechanical properties

Tensile Modulus	10000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	110 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2 %	ISO 527-1/-2
Charpy impact strength, 23°C	40 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	8.5 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
-------------------------------	--------	----------------

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	UL 94
Burning Behav. at thickness h	V-0 class	UL 94
Thickness tested	0.4 mm	UL 94
UL recognition	yes	UL 94

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
--------------------------	-------	----------------

Injection

Drying Temperature	140 - 120 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	0.01 %
Max. regrind level	25 %
Max. mould temperature	80 - 100 °C
Hold pressure range	40 - 120 MPa
Back pressure	3 MPa
Injection speed	fast

CELANEX® XFR 6842 GF30 HRCT (PRELIMINARY)

Characteristics

Additives

Release agent, Flame retardant

Additional information

Injection molding

Melt Temperature. 255-270 °C
Mold Temperature *): 80-100 °C
Maximum Barrel Residence Time **): 5 min
Injection Speed: high
Peripheral screw speed: max. 0.25 m/sec
Back Pressure: 10-30 bar
Injection Pressure: 600-1500 bar
Holding Pressure: 400-1200 bar

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided. For grades containing flame retardants, a maximum temperature of 270 °C should not be exceeded.

Ticona recommends only externally heated hot runner systems.

*) For moulded parts with especially high requirements to the surface quality or dimensional stability, a mold temperature of up to 120 °C can be advantageous.

**) If the cylinder temperatures are higher than the recommended maximum temperatures, the max. residence time in the barrel has to be reduced.

Processing Texts

Pre-drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level of less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250-285 °F (140 - 120 °C) for 4 - 6 hours.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to < 100 °C.

Injection molding

Melt Temperature. 255-270 °C
Mold Temperature *): 80-100 °C
Maximum Barrel Residence Time **): 5 min
Injection Speed: high
Peripheral screw speed: max. 0.25 m/sec
Back Pressure: 10-30 bar
Injection Pressure: 600-1500 bar
Holding Pressure: 400-1200 bar

CELANEX® XFR 6842 GF30 HRCT (PRELIMINARY)

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided. For grades containing flame retardants, a maximum temperature of 270 °C should not be exceeded.

Ticona recommends only externally heated hot runner systems.

*) For moulded parts with especially high requirements to the surface quality or dimensional stability, a mold temperature of up to 120 °C can be advantageous.

**) If the cylinder temperatures are higher than the recommended maximum temperatures, the max. residence time in the barrel has to be reduced.

Injection molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level of less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250-285 °F (140-120 °C) for 4-6 hours.
