

HOSTAFORM® MT®8F01

Low level PTFE filled with good flow for medical technology applications

Hostaform® MT®8F01 is a standard flow low level polytetrafluoroethylene filled (PTFE) product designed for use in wear applications against plastics, metal, glass or ceramic mating surfaces where silicone lubricants can not be tolerated.

Hostaform® MT®8F01 is a special grade developed for medical industry applications and complies with:

- CFR 21 (177.2470) of the Food and Drug Administration (FDA) and is listed in the Drug Master File (DMF 11559) and the Device Master File (MAF 1079)
- the corresponding EU and national registry requirements
- biocompatibility in tests corresponding to USP <88> Class VI/ISO 10993
- low residual monomers
- no animal-derived constituents

Rheological properties

Melt volume-flow rate	7.9 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Modulus	2600 MPa	ISO 527-1/-2
Yield stress, 50mm/min	58 MPa	ISO 527-1/-2
Yield strain, 50mm/min	9 %	ISO 527-1/-2
Nominal strain at break	28 %	ISO 527-1/-2
Charpy notched impact strength, 23°C	5.2 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	166 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	102 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120 E-6/K	ISO 11359-1/-2

Other properties

Density	1440 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	100 - 120 °C	
Drying Time, Dehumidified Dryer	3 - 4 h	
Melt Temperature Optimum	190 °C	Internal
Max. mould temperature	77 - 93 °C	
Back pressure	2 MPa	


HOSTAFORM® MT®8F01

Characteristics

Additives


Release agent

Stress-strain




HOSTAFORM® MT®8F01

Secant modulus-strain



HOSTAFORM® MT®8F01

True stress-strain



HOSTAFORM® MT® 8F01

Processing Texts

Pre-drying

Drying is not normally required. If material has come in contact with moisture through improper storage or handling, drying may be necessary to prevent splay and odor problems.