

HOSTAFORM® S 9244 XAP® 2

HOSTAFORM®

POM copolymer, modified Injection molding type, elastomer-containing; with higher impact strength and slightly lower hardness, rigidity and chemical resistance than unmodified acetal copolymer. Reduced emission grade, Emission according to VDA 275 < 5 mg/kg good weld strength. Preliminary Datasheet

Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

Rheological properties

Melt volume-flow rate	1.4 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage, parallel	1.7 %	ISO 294-4, 2577
Moulding shrinkage, normal	1.6 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	1450 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	33 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	7 %	ISO 527-1/-2
Nominal strain at break	>50 %	ISO 527-1/-2
Flexural modulus	1450 MPa	ISO 178
Tensile creep modulus, 1h	1200 MPa	ISO 899-1
Tensile creep modulus, 1000h	650 MPa	ISO 899-1
Charpy impact strength, 23 °C	N kJ/m ²	ISO 179/1eU
Charpy impact strength, -30 °C	200 ^[P] kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	18 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30 °C	12 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.43 ^[C]	

[P]: Partial Break

[C]: Calculated

Thermal properties

Melting temperature, 10 °C/min	166 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	68 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	130 E-6/K	ISO 11359-1/-2

Electrical properties

Relative permittivity, 100Hz	3.6	IEC 62631-2-1
Relative permittivity, 1MHz	3.6	IEC 62631-2-1
Dissipation factor, 100Hz	40 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	60 E-4	IEC 62631-2-1
Volume resistivity	1E11 Ohm.m	IEC 62631-3-1
Surface resistivity	1E13 Ohm	IEC 62631-3-2
Comparative tracking index	600	IEC 60112

HOSTAFORM® S 9244 XAP® 2

HOSTAFORM®

Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	1.2 %	Sim. to ISO 62
Density	1260 kg/m ³	ISO 1183

Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	195 °C
Min. melt temperature	190 °C
Max. melt temperature	200 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	80 °C
Hold pressure range	60 - 120 MPa
Back pressure	2 MPa

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent
Special characteristics	Low emissions, Improved weld line

Additional information

Injection molding

Processing

Above pressures, including back pressure, are given as specific or plastic pressures. The back pressure on Hostaform® and Celcon® POM materials should be as low as possible, just enough to remove air from the pellets during feeding.

Processing Notes

Pre-Drying

It is normally not necessary to dry HOSTAFORM. However, should there be surface moisture (condensate) on the molding compound as a result of incorrect storage, drying is required. A circulating air drying cabinet can be used for this purpose

Storage

The product can then be stored in standard conditions until processed.

HOSTAFORM® S 9244 XAP® 2

HOSTAFORM®


Automotive

OEM
Mercedes-Benz
Renault

STANDARD
DBL5404
UB15, No Spec, Special Part Approval, See
Your CE Account Manager.

ADDITIONAL INFORMATION
BQF


Stress-strain



HOSTAFORM® S 9244 XAP®2

HOSTAFORM®


Secant modulus-strain



HOSTAFORM® S 9244 XAP®2

HOSTAFORM®


Stress-strain, 50mm/min



HOSTAFORM® S 9244 XAP®2

HOSTAFORM®

Secant modulus-strain, 50mm/min



Printed: 2025-05-30

Page: 6 of 6

Revised: 2024-12-03 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.