

(+) 18816996168

Poncioplastics.com



POLIFOR C12 TE/20 NEGRO 900 X1 - PP

Physical properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183
Melt flow rate, MFR	10	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133
Mechanical properties	Value	Unit	Test Standard
Flexural modulus, 23°C	1600	MPa	ISO 178
Izod impact notched, 23°C	7	kJ/m ²	ISO 180/1A
Thermal properties	Value	Unit	Test Standard
Vicat softening temperature, 50°C/h 50N	70	°C	ISO 306