

TECNOPRENE® 3K2

Polypropylene, copolymer, 10% glass fiber reinforced, chemically coupled.

Typical mechanical properties

Tensile Modulus	2700 MPa	ISO 527-1/-2
Stress at break, 5mm/min	40 MPa	ISO 527-1/-2
Strain at break, 5mm/min	4 %	ISO 527-1/-2
Flexural Modulus	2500 MPa	ISO 178
Flexural Strength	65 MPa	ISO 178
Charpy notched impact strength, 23°C	9.5 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	10 kJ/m ²	ISO 180/1A

Thermal properties

Temp. of deflection under load, 1.8 MPa	112 °C	ISO 75-1/-2
---	--------	-------------

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94

Other properties


Density	970 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	50 - 80 °C


TECNOPRENE® 3K2

Stress-strain



TECNOPRENE® 3K2

Secant modulus-strain



TECNOPRENE® 3K2

Processing Texts

Longer pre-drying times/storage

This product should be stored in a covered facility and kept away from moisture and heat.
