

FORTRON® 1140L4 HR

Polyphenylene sulfide

Fortron 1140L4 HR is a 40% glass-reinforced grade with improved hydrolysis resistance. It is the strongest and toughest product available. It exhibits excellent heat and chemical resistance, good electrical properties and is inherently flame-retardant. The high hardness and rigidity at elevated temperatures allows for good load bearing performance. This product has good weldability due to the modest filler level. Applications made of this grade are electrical components (i.e. bobbins, lamp housings, brush holders) and various other components requiring strength and resistance to aggressive chemicals (i.e. automotive heaters, pumps, valves, fuel rails, microwave oven rings and distillation column packings).

Product information

Resin Identification	PPS-GF40	ISO 1043
Part Marking Code	>PPS-GF40<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.3 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.6 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	15600 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	200 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.8 %	ISO 527-1/-2
Flexural modulus	14600 MPa	ISO 178
Flexural strength	290 MPa	ISO 178
Charpy notched impact strength, 23 °C	10 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	8.5 kJ/m ²	ISO 180/1A
Izod impact strength, 23 °C	58.7 kJ/m ²	ISO 180/1U
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10 °C/min	280 °C	ISO 11357-1/-3
Glass transition temperature, 10 °C/min	90 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	270 °C	ISO 75-1/-2
Thermal conductivity, flow	0.47 W/(m K)	ISO 22007-2
Thermal conductivity, crossflow	0.41 W/(m K)	ISO 22007-2
Thermal conductivity, through plane	0.39 W/(m K)	ISO 22007-2
Effective thermal diffusivity, flow	2.7E-7 m ² /s	ISO 22007-4
Effective thermal diffusivity, crossflow	2.4E-7 m ² /s	ISO 22007-4
Effective thermal diffusivity, through plane	2.2E-7 m ² /s	ISO 22007-4
Specific heat capacity of melt	1040 J/(kg K)	ISO 22007-4

Flammability

Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
Thickness tested	0.38 mm	IEC 60695-11-10
Oxygen index	47 %	ISO 4589-1/-2

FORTRON® 1140L4 HR

Polyphenylene sulfide

Electrical properties

Volume resistivity	1E15 Ohm.m	IEC 62631-3-1
Arc Resistance	134 s	UL 746B

Physical/Other properties

Water absorption, 2mm	0.02 %	Sim. to ISO 62
Water absorption, Immersion 24h	0.02 %	Sim. to ISO 62
Density	1600 kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	130 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.02 %
Melt Temperature Optimum	330 °C
Min. melt temperature	310 °C
Max. melt temperature	340 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	150 °C
Min. mould temperature	140 °C
Max. mould temperature	160 °C
Hold pressure range	30 - 70 MPa
Back pressure	3 MPa

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Additives	Release agent
Special characteristics	Flame retardant, Heat stabilised or stable to heat, Hydrolysis resistant, Chemical resistant

Additional information

Injection molding

Preprocessing

Predrying in a dehumidified air dryer at 130 - 140 degC/3-4 hours is recommended.

Processing

On injection molding machines with 15-25 D long three-section screws, as are usual in the trade, the FORTRON is processable. A shut-off nozzle is preferred to a free-flow nozzle.

Melt temperature 320-340 degC
Mold wall temperature at least 140 degC

FORTRON® 1140L4 HR

Polyphenylene sulfide

A medium injection rate is normally preferred. All mold cavities must be effectively vented.

Postprocessing

Tool temperature of at least 135 degC is recommended for parts to achieve maximum crystallizable potential.

Processing Notes

Pre-Drying

FORTRON should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Storage

For subsequent storage the material should be stored dry in the dryer until processed ($\leq 60\text{ h}$).