

# SOFPRENE® 54R300A72/CT NEUTRO

## Typical mechanical properties

|                       |           |                        |
|-----------------------|-----------|------------------------|
| Stress at break       | 595 psi   | ISO 527-1/-2 or ISO 37 |
| Elongation at break   | 500 %     | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 3s  | 73        | ISO 48-4 / ISO 868     |
| Tear strength, normal | 143 lb/in | ISO 34-1               |

## Other properties

|         |          |          |
|---------|----------|----------|
| Density | 9 lb/gal | ISO 1183 |
|---------|----------|----------|

## Injection

|                        |             |
|------------------------|-------------|
| Max. mould temperature | 68 - 104 °F |
|------------------------|-------------|