

TECHNICAL DATA SHEET

RILSAMID® AZM 30 O TLD

POLYAMIDE 12 PELLET

RILSAMID® AZM 30 O TLD resin is a polyamide 12 compound. This glass fiber reinforced grade is designed for injection molding and is used to produce automotive fittings & quick connectors.

Designation : ISO 16396 - PA12, GF30, M1G1HLR, C16-070

TYPE

PA12-GF30

MAIN APPLICATIONS

- Auto - Fluid Connectors

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Injection Molding

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Release agent

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	12	cm³/10min	ISO 1133
Shrinkage, Parallel (t+24h)	0.2	%	ISO 294-4
Shrinkage, Normal (t+24h)	0.8	%	ISO 294-4

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Tensile modulus, 23°C (73°F), 1 mm/min	6700 / 6300	MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	127 / 115	MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	4 / 4	%	ISO 527-1/-2
Charpy unnotched impact strength, 23°C (73°F)	85 / 88	kJ/m2	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	96 / 93	kJ/m2	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 23	kJ/m2	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	15 / 16	kJ/m2	ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

RILSAMID® AZM 30 0 TLD

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	179	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	165	°C	ISO 306
Heat deflection temperature, 0.45 MPa	175	°C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	160	°C	ISO 75-1/-2
Thermal degradation temperature, Under nitrogen at 10°C/min (1%_wt_Loss)	222	°C	ISO 11358-1
Thermal degradation temperature, Under air at 10°C/min (1%_wt_Loss)	224	°C	ISO 11358-1

ELECTRICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Surface resistivity, 23°C (73°F)	- / 1.0E+14	Ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73°F)	- / 1.0E+11	Ohm.m	IEC 62631-3-1
Comparative tracking index, 23°C (73°F)	- / 600		IEC 60112
Dielectric stress, 23°C (73°F)	- / 45	kV/mm	IEC 60243-1
Relative permittivity, 100Hz	- / 4		IEC 62631-2-1
Relative permittivity, 1Mhz	- / 4		IEC 62631-2-1
Dissipation factor, 100Hz	- / 752	E-4	IEC 62631-2-1
Dissipation factor, 1Mhz	- / 752	E-4	IEC 62631-2-1

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Specific gravity, 23°C (73°F)	1.23	g/cm ³	ISO 1183-1
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.6	%	ISO 62
Water absorption, 23°C (73°F), immersion, equilibrium	1.2	%	ISO 62

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 40-90°C (105-195°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

RILSAMID® AZM 30 O TLD

DIAGRAMS

