



## Bergaflex™ BFI 70A-302

### Thermoplastic Elastomer

#### Key Characteristics

##### Product Description

Bergaflex™ BFI 70A-302 is an easy processing, general purpose TPE.

##### General

Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• General Purpose • Good Flow • Good Processability • Good Processing Stability
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

#### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.17	1.17	ISO 1183
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>2, 3</sup> (Break, 73°F (23°C))	899 psi	6.20 MPa	DIN 53504
Tensile Elongation <sup>2, 3</sup> (Break, 73°F (23°C))	640 %	640 %	DIN 53504
Compression Set (73°F (23°C), 72 hr)	19 %	19 %	ISO 815
Compression Set			ISO 815
158°F (70°C), 22 hr	42 %	42 %	
212°F (100°C), 22 hr	80 %	80 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	70	70	ISO 7619

#### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	338 to 347 °F	170 to 175 °C
Middle Temperature	338 to 374 °F	170 to 190 °C
Front Temperature	365 to 392 °F	185 to 200 °C
Nozzle Temperature	374 to 392 °F	190 to 200 °C
Mold Temperature	86 to 122 °F	30 to 50 °C
Back Pressure <sup>4</sup>	290 to 1450 psi	2.00 to 10.0 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

**Injection Notes**

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Bergaflex™ BFI 70A-3106 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 3 in/sec

1st Stage - Boost Pressure: 350 to 900 psi

2nd Stage - Hold Pressure: 30% of Boost

Hold Time (Thick Part): 3 to 10 sec

Hold Time (Thin Part): 1 to 3 sec

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 7.9 in/min (200 mm/min)

<sup>3</sup> Specimen type S2

<sup>4</sup> If you use color masterbatches, higher back pressure is necessary.

The logo for PolyOne, featuring the word "PolyOne" in a stylized, italicized serif font with a trademark symbol. A horizontal line is drawn underneath the text.

*Beyond Polymers.*

*Better Business Solutions. <sup>SM</sup>*