



Dynaflex™ G2701-1000-02

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex™ G2701-1000-02 is an easy processing TPE designed for injection molding and extrusion applications that require FDA compliance.

- Adhesion to Polypropylene
- Excellent Colorability
- High Flow For Long, Thin-Wall Parts
- Rubbery Feel
- Soft touch

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Latin America • North America	
Features	• Good Colorability • High Flow	• Ozone Resistant • Recyclable Material	• UV Resistant
Uses	• Consumer Applications • Overmolding	• Personal Care • Thin-walled Parts	• Transparent or Translucent Parts
Agency Ratings	• FDA 21 CFR 177.2600 ¹		
RoHS Compliance	• RoHS Compliant		
Appearance	• Translucent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.900	0.900	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	13 g/10 min	13 g/10 min	
200°C/5.0 kg	61 g/10 min	61 g/10 min	
Molding Shrinkage - Flow	5.0E-3 to 0.011 in/in	0.50 to 1.1 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{3,4} (100% Strain, 73°F (23°C))	490 psi	3.38 MPa	ASTM D412
Tensile Stress ^{3,4} (300% Strain, 73°F (23°C))	643 psi	4.43 MPa	ASTM D412
Tensile Strength ^{3,4} (Break, 73°F (23°C))	1100 psi	7.58 MPa	ASTM D412
Tensile Elongation ^{3,4} (Break, 73°F (23°C))	680 %	680 %	ASTM D412
Tear Strength	240 lbf/in	42.0 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	24 %	24 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	66	66	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec ⁻¹	11.0 Pa·s	11.0 Pa·s	

Additional Information

Dynaflex™ G2701-1000-02 can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times.

Municipality waste stream recycle code is "7" which is designated for "Other".

Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	270 to 340 °F	132 to 171 °C
Middle Temperature	310 to 380 °F	154 to 193 °C
Front Temperature	335 to 405 °F	168 to 207 °C
Nozzle Temperature	335 to 405 °F	168 to 207 °C
Mold Temperature	60 to 80 °F	16 to 27 °C
Back Pressure	50.0 to 150 psi	0.345 to 1.03 MPa
Screw Speed	25 to 75 rpm	25 to 75 rpm

Injection Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (LDPE) carriers are most suitable for coloring Dynaflex™ G2701-1000-02. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G2701-1000-02 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynaflex™ G2701-1000-02 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 5 in/sec
 1st Stage - Boost Pressure: 250 to 650 psi
 2nd Stage - Hold Pressure: 70% of Boost
 Hold Time (Thick Part): 4 to 10 sec
 Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.

² Typical values are not to be construed as specifications.

³ Die C

⁴ 2 hr