



Dynaflex™ G7430-9001-00

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex™ G7430-9001-00 is an easy processing, high performance compound designed for use in applications requiring tough, durable material.

- Excellent Heat Stability
- Good Ozone and UV Stability
- Overmold Adhesion to Polypropylene
- Suitable for Outdoor Use

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Thermal Stability • High Strength	• Ozone Resistant • Recyclable Material	• UV Resistant
Uses	• Appliance Components • Consumer Applications	• Overmolding • Sporting Goods	• Strain Reliefs
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.920	0.920	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.018 to 0.022 in/in	1.8 to 2.2 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{2, 3} (100% Strain, 73°F (23°C))	360 psi	2.48 MPa	ASTM D412
Tensile Stress ^{2, 3} (300% Strain, 73°F (23°C))	590 psi	4.07 MPa	ASTM D412
Tensile Strength ^{2, 3} (Break, 73°F (23°C))	1300 psi	8.96 MPa	ASTM D412
Tensile Elongation ^{2, 3} (Break, 73°F (23°C))	650 %	650 %	ASTM D412
Tear Strength	210 lbf/in	36.8 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	17 %	17 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	68	68	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec ⁻¹	12.6 Pa·s	12.6 Pa·s	ASTM D3835

Additional Information

Dynaflex™ G7430-9001-00 can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times.

Municipality waste stream recycle code is "7" which is designated for "Other".

Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	335 to 350 °F	168 to 177 °C
Middle Temperature	350 to 370 °F	177 to 188 °C
Front Temperature	370 to 440 °F	188 to 227 °C
Nozzle Temperature	370 to 440 °F	188 to 227 °C
Back Pressure	50.0 to 150 psi	0.345 to 1.03 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

Injection Notes

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G7430-9001-00 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Drying is not Required

Injection Speed: 1 to 5 in/sec
 1st Stage - Boost Pressure: 250 to 650 psi
 2nd Stage - Hold Pressure: 50% of Boost
 Hold Time (Thick Part): 4 to 10 sec
 Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Typical values are not to be construed as specifications.

² Die C

³ 2 hr