



Dynaflex™ G7736-1

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex™ G7736-1 is a general purpose compound designed to provide easy processing and a good surface finish.

- Good Aesthetics
- Good Ozone/UV Stability
- High Flow for Thin-Wall Parts
- Overmold Adhesion To Polypropylene
- Rubbery Feel
- Soft Touch

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Colorability • High Flow	• Ozone Resistant • Recyclable Material	• UV Resistant
Uses	• Consumer Applications • General Purpose	• Overmolding • Soft Touch Applications	• Sporting Goods • Thin-walled Parts
Agency Ratings	• FDA 21 CFR 177.1210 ¹		
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20 g/10 min	20 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.022 to 0.026 in/in	2.2 to 2.6 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{3,4} (100% Strain, 73°F (23°C))	150 psi	1.03 MPa	ASTM D412
Tensile Stress ^{3,4} (300% Strain, 73°F (23°C))	247 psi	1.70 MPa	ASTM D412
Tensile Strength ^{3,4} (Break, 73°F (23°C))	437 psi	3.01 MPa	ASTM D412
Tensile Elongation ^{3,4} (Break, 73°F (23°C))	660 %	660 %	ASTM D412
Tear Strength	80.0 lbf/in	14.0 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	11 %	11 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	36	36	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec ⁻¹	5.30 Pa·s	5.30 Pa·s	ASTM D3835

Additional Information

Dynaflex™ G7736-1 can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times.

Municipality waste stream recycle code is "7" which is designated for "Other".

Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	330 to 360 °F	166 to 182 °C
Middle Temperature	360 to 400 °F	182 to 204 °C
Front Temperature	370 to 410 °F	188 to 210 °C
Nozzle Temperature	380 to 430 °F	193 to 221 °C
Mold Temperature	60 to 80 °F	16 to 27 °C
Back Pressure	0.00 to 125 psi	0.00 to 0.862 MPa
Screw Speed	25 to 75 rpm	25 to 75 rpm

Injection Notes

Color concentrates with Polypropylene (PP), Ethylene Vinyl Acetate (EVA), or Low Density Polyethylene (LDPE) carrier are most suitable for coloring Dynaflex™ G7736-1. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25-40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by the use of precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G7736-1 with minimal property losses, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynaflex™ G7736-1 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 1 to 5 in/sec
 1st Stage - Boost Pressure: 100 to 800 psi
 2nd Stage - Hold Pressure: 30% of Boost
 Hold Time (Thick Part): 4 to 10 sec
 Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.

² Typical values are not to be construed as specifications.

³ Die C

⁴ 2 hr