



Dynaflex™ G7940-1001-00

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynaflex™ G7940-1001-00 is an easy processing, general purpose TPE designed for a wide variety of applications, including those where FDA compliance is required.

- Non-Slip Grip
- Overmold Adhesion to Polypropylene
- Soft Touch, Rubbery Feel

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose • Good Colorability	• Good Flow • Good Processability	• Good Processing Stability • Recyclable Material
Uses	• Consumer Applications • Flexible Grips • Gaskets	• General Purpose • Household Goods • Overmolding	• Seals • Soft Touch Applications • Sporting Goods
Agency Ratings	• FDA 21 CFR 177.2600 ¹	• UL 94	
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FMVSS 302		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.18	1.18	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.013 to 0.021 in/in	1.3 to 2.1 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{3,4} (100% Strain, 73°F (23°C))	180 psi	1.24 MPa	ASTM D412
Tensile Stress ^{3,4} (300% Strain, 73°F (23°C))	295 psi	2.03 MPa	ASTM D412
Tensile Strength ^{3,4} (Break, 73°F (23°C))	520 psi	3.59 MPa	ASTM D412
Tensile Elongation ^{3,4} (Break, 73°F (23°C))	580 %	580 %	ASTM D412
Tear Strength	100 lbf/in	17.5 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	12 %	12 %	ASTM D395B
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	40	40	ASTM D2240
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.5 mm))	HB	HB	UL 94
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec ⁻¹	8.80 Pa·s	8.80 Pa·s	ASTM D3835

Additional Information

Dynaflex™ G7940-1001-00 can be recycled as a filler or impact modifier for polyolefins, or can be recycled by grinding and reintroduction to the molding process. Similar to PP or PE recycling process, if separated appropriately, it can be recycled many times.

Municipality waste stream recycle code is "7" which is designated for "Other".

Please contact GLS Thermoplastic Elastomers for a copy of our Recyclability Compliance letter.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	320 to 370 °F	160 to 188 °C
Middle Temperature	350 to 380 °F	177 to 193 °C
Front Temperature	360 to 410 °F	182 to 210 °C
Nozzle Temperature	380 to 420 °F	193 to 216 °C
Mold Temperature	60 to 100 °F	16 to 38 °C
Back Pressure	0.00 to 100 psi	0.00 to 0.689 MPa
Screw Speed	25 to 100 rpm	25 to 100 rpm

Injection Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Dynaflex™ G7940-1001-00. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G7940-1001-00 with minimal property losses, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should be as low as possible. The final determination of regrind effectiveness should be determined by the customer.

The Dynaflex™ G7940-1001-00 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

- Injection Speed: 1 to 3 in/sec
- 1st Stage - Boost Pressure: 175 to 800 psi
- 2nd Stage - Hold Pressure: 30% of Boost
- Hold Time (Thick Part): 3 to 10 sec
- Hold Time (Thin Part): 1 to 3 sec

Notes

- ¹ Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.
- ² Typical values are not to be construed as specifications.
- ³ Die C
- ⁴ 2 hr