



Geon™ HTX M6230

Polyvinyl Chloride Alloy

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• High Flow	• Medium Impact Resistance
Uses	• Appliances • Business Equipment	• Construction Applications • Electrical/Electronic Applications	• General Purpose • Telecommunications
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.23	1.23	ASTM D792
Spiral Flow	29.0 in	73.7 cm	
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3 in/in	0.20 to 0.50 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	340000 psi	2340 MPa	ASTM D638
Tensile Strength ² (Yield)	6300 psi	43.4 MPa	ASTM D638
Tensile Elongation ² (Break)	15 %	15 %	ASTM D638
Flexural Modulus	350000 psi	2410 MPa	ASTM D790
Flexural Strength	11000 psi	75.8 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
32°F (0°C), 0.125 in (3.18 mm), Injection Molded	1.0 ft·lb/in	53 J/m	
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	2.0 ft·lb/in	110 J/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	80	80	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	180 °F	82.2 °C	
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Annealed, 0.250 in (6.35 mm)	198 °F	92.2 °C	
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	172 °F	77.8 °C	
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Annealed, 0.250 in (6.35 mm)	194 °F	90.0 °C	
RTI Elec	122 °F	50.0 °C	UL 746
RTI Imp	122 °F	50.0 °C	UL 746
RTI Str	122 °F	50.0 °C	UL 746

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.0590 in (1.50 mm), ALL)	V-0 5VA	V-0 5VA	UL 94
CSA Flammability ³			
58.0 mil (1.47 mm)	V-0	V-0	
61.0 mil (1.55 mm)	5VA	5VA	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	400 to 410 °F	204 to 210 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 2.0 in/min (51 mm/min)

³ All Colors

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbaastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giallewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.