



Geon™ HTX Ultra LA425

Polyvinyl Chloride Alloy

Key Characteristics

Product Description	
Optimum for Black and Darker Colors below 50L value.	
General	
Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Features	• Good Weather Resistance • High Impact Resistance • High Stiffness
Uses	• Outdoor Applications • Profiles
Forms	• Pellets
Processing Method	• Extrusion

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.22	1.22	ASTM D792
PVC Cell Classification	4-42411-64-0000	4-42411-64-0000	ASTM D4216
PVC Cell Classification	15225	15225	ASTM D1784
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	289000 psi	1990 MPa	ASTM D638
Tensile Strength ² (Yield)	5490 psi	37.9 MPa	ASTM D638
Flexural Modulus	302000 psi	2080 MPa	ASTM D790
Flexural Strength	9590 psi	66.1 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	14 ft·lb/in	720 J/m	ASTM D256A
Drop Impact Resistance 73°F (23°C) ³	1.50 in·lb/mil	66.7 J/cm	ASTM D4226
73°F (23°C) ⁴	4.00 in·lb/mil	178 J/cm	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 15 sec)	74	74	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	195 °F	90.6 °C	ASTM D648
Deflection Temperature Under Load 66 psi (0.45 MPa), Annealed, 0.125 in (3.18 mm)	196 °F	91.1 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	183 °F	83.9 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed, 0.125 in (3.18 mm)	189 °F	87.2 °C	ASTM D648
CLTE - Flow	4.8E-5 in/in/°F	8.6E-5 cm/cm/°C	ASTM D696

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Additional Information	Typical Value (English)	Typical Value (SI)
Ease of Sizing	Acceptable	Acceptable
Recommend drying material for a minimum of 2 hours at 160 degrees Fahrenheit.		
Ductile/Brittle transition as measured by Instrumented Impact is 5 deg.C Physical properties based on Geon HTX Ultra LA425 Natural 0000		

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	345 to 380 °F	174 to 193 °C

Notes

- ¹ Typical values are not to be construed as specifications.
- ² Type I, 0.20 in/min (5.1 mm/min)
- ³ Procedure A, C.125 Dart
- ⁴ Procedure B, C.125 Dart

CONTACT INFORMATION

Americas	Asia	Europe
United States - Avon Lake +1 440 930 1000	China - Guangzhou +86 20 8732 7260	Germany - Gaggenau +49 7225 6802 0
United States - McHenry +1 815 385 8500	China - Shenzhen +86 755 2969 2888	Spain - Barbastró (Huesca) +34 974 310 314
	China - Suzhou +86 512 6823 24 38	
	China - Suzhou +86 512 6265 2600	
	Hong Kong - +852 2690 5332	
	Taiwan - Yonghe City, +886 9396 99740, +886 2929 1849	



Beyond Polymers.
Better Business Solutions. SM
www.polyone.com

PolyOne Americas	PolyOne Asia	PolyOne Europe
33587 Walker Road Avon Lake, Ohio 44012 United States +1 440 930 1000 +1 866 POLYONE	No. 88 Guoshoujing Road Z.J Hi-tech Park, Pudong Shanghai, 201203, China +86 21 5080 1188	6 Gälllewee +352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.