



# Geon™ Vinyl Fittings M1150

## Rigid Polyvinyl Chloride

### Key Characteristics

General			
Material Status	• Commercial: Active <sup>1</sup>		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Medium Flow		
Uses	• Fittings		
Agency Ratings	• NSF 14	• NSF 61	
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>2</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.39	1.39	ASTM D792
PVC Cell Classification	16354	16354	ASTM D1784
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>3</sup>	400000 psi	2760 MPa	ASTM D638
Tensile Strength <sup>3</sup> (Yield)	6690 psi	46.1 MPa	ASTM D638
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	22 ft-lb/in	1200 J/m	ASTM D256A
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	80	80	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed, 0.250 in (6.35 mm)	158 °F	70.1 °C	ASTM D648

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	390 to 410 °F	199 to 210 °C

### Notes

<sup>1</sup> RoHS compliant

<sup>2</sup> Typical values are not to be construed as specifications.

<sup>3</sup> Type I, 0.20 in/min (5.1 mm/min)

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

**CONTACT INFORMATION**

**Americas**

United States - Avon Lake  
+1 440 930 1000

United States - McHenry  
+1 815 385 8500

**Asia**

China - Guangzhou  
+86 20 8732 7260

China - Shenzhen  
+86 755 2969 2888

China - Suzhou  
+86 512 6823 24 38

China - Suzhou  
+86 512 6265 2600

Hong Kong -  
+852 2690 5332

Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1849

**Europe**

Germany - Gaggenau  
+49 7225 6802 0

Spain - Barbastro (Huesca)  
+34 974 310 314



*Beyond Polymers.*

*Better Business Solutions.™*

[www.polyone.com](http://www.polyone.com)

**PolyOne Americas**

33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE

**PolyOne Asia**

No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188

**PolyOne Europe**

6 Giällewee  
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.