



Geon™ Vinyl Rigid Extrusion 87350

Rigid Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose		
Uses	• General Purpose	• Outdoor Applications	
Forms	• Pellets		
Processing Method	• Sheet Extrusion		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.44	1.44	ASTM D792
PVC Cell Classification	1-41332-23	1-41332-23	ASTM D4216
PVC Cell Classification	15343	15343	ASTM D1784
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	360000 psi	2480 MPa	ASTM D638
Tensile Strength ² (Yield)	6290 psi	43.4 MPa	ASTM D638
Flexural Modulus	355000 psi	2450 MPa	ASTM D790
Flexural Strength	10200 psi	70.3 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	12 ft·lb/in	630 J/m	
Across Flow : 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	16 ft·lb/in	880 J/m	
Flow : 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	14 ft·lb/in	720 J/m	
Drop Impact Resistance			ASTM D4226
73°F (23°C) ³	1.47 in·lb/mil	65.4 J/cm	
73°F (23°C) ⁴	2.93 in·lb/mil	130 J/cm	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 15 sec)	82	82	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	154 °F	67.8 °C	
CLTE - Flow	4.1E-5 in/in/°F	7.3E-5 cm/cm/°C	ASTM D696
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.0354 in (0.899 mm), ALL	V-0	V-0	
0.118 in (3.00 mm), ALL	5VA	5VA	

Additional Information

Note: The Cell Classification was determined using the notched Izod test with injection molded samples.

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	370 to 400 °F	188 to 204 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

³ Procedure A, C.125 Dart

⁴ Procedure B, C.125 Dart

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbaastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.