



Geon™ Vinyl Rigid Molding M3800

Rigid Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• High Flow	• High Impact Resistance
Uses	• Appliances • Business Equipment	• Construction Applications • Electrical/Electronic Applications	• General Purpose • Telecommunications
Agency Ratings	• NSF 51	• NSF 61	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.33	1.33	ASTM D792
Spiral Flow	44.0 in	112 cm	
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3 in/in	0.20 to 0.50 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	330000 psi	2280 MPa	ASTM D638
Tensile Strength ² (Yield)	6000 psi	41.4 MPa	ASTM D638
Tensile Elongation ² (Break)	35 %	35 %	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790
Flexural Strength	9700 psi	66.9 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
0°F (-18°C), 0.125 in (3.18 mm), Injection Molded	2.0 ft·lb/in	110 J/m	
32°F (0°C), 0.125 in (3.18 mm), Injection Molded	5.0 ft·lb/in	270 J/m	
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	12 ft·lb/in	640 J/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	79	79	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	162 °F	72.2 °C	
66 psi (0.45 MPa), Annealed, 0.250 in (6.35 mm)	167 °F	75.0 °C	ASTM D648
264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	156 °F	68.9 °C	ASTM D648
264 psi (1.8 MPa), Annealed, 0.250 in (6.35 mm)	163 °F	72.8 °C	ASTM D648

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
RTI Elec	194 °F	90.0 °C	UL 746
RTI Imp	185 °F	85.0 °C	UL 746
RTI Str	194 °F	90.0 °C	UL 746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.0550 in (1.40 mm), ALL	V-0	V-0	
0.0630 in (1.60 mm), ALL	5VA	5VA	
Additional Information	Typical Value (English)	Typical Value (SI)	
CSA Flammability ³ (63.0 mil (1.60 mm))	• V-0 • 5VA	• V-0 • 5VA	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	390 to 410 °F	199 to 210 °C

Notes

- ¹ Typical values are not to be construed as specifications.
- ² Type I, 2.0 in/min (51 mm/min)
- ³ All Colors

CONTACT INFORMATION

Americas	Asia	Europe
United States - Avon Lake +1 440 930 1000	China - Guangzhou +86 20 8732 7260	Germany - Gaggenau +49 7225 6802 0
United States - McHenry +1 815 385 8500	China - Shenzhen +86 755 2969 2888	Spain - Barbastro (Huesca) +34 974 310 314
	China - Suzhou +86 512 6823 24 38	
	China - Suzhou +86 512 6265 2600	
	Hong Kong - +852 2690 5332	
	Taiwan - Yonghe City, +886 9396 99740, +886 2929 1849	



Beyond Polymers.
Better Business Solutions. SM
www.polyone.com

PolyOne Americas	PolyOne Asia	PolyOne Europe
33587 Walker Road Avon Lake, Ohio 44012 United States +1 440 930 1000 +1 866 POLYONE	No. 88 Guoshoujing Road Z.J Hi-tech Park, Pudong Shanghai, 201203, China +86 21 5080 1188	6 Gälllewee +352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.