



Geon™ Vinyl Rigid Extrusion 87160

Rigid Polyvinyl Chloride

Key Characteristics

| General | | | |
|-----------------------|---|-----------------------------|-----------------|
| Material Status | • Commercial: Active | | |
| Regional Availability | • Africa & Middle East • Asia Pacific | • Europe • Latin America | • North America |
| Features | • General Purpose • High Impact Resistance | | |
| Uses | • General Purpose • Profiles | | |
| Agency Ratings | • NSF STD-51 | | |
| Forms | • Pellets | | |
| Processing Method | • Extrusion | | |

Technical Properties ¹

| Physical | Typical Value (English) | Typical Value (SI) | Test Method |
|---|-------------------------|--------------------|-------------|
| Density / Specific Gravity | 1.40 | 1.40 | ASTM D792 |
| PVC Cell Classification | 13354 | 13354 | ASTM D1784 |
| Mechanical | Typical Value (English) | Typical Value (SI) | Test Method |
| Tensile Modulus ² | 420000 psi | 2890 MPa | ASTM D638 |
| Tensile Strength ² (Yield) | 6340 psi | 43.7 MPa | ASTM D638 |
| Flexural Modulus | 419000 psi | 2890 MPa | ASTM D790 |
| Flexural Strength | 11900 psi | 82.3 MPa | ASTM D790 |
| Impact | Typical Value (English) | Typical Value (SI) | Test Method |
| Notched Izod Impact | | | ASTM D256A |
| Across Flow : 73°F (23°C), 0.125 in (3.18 mm), Compression Molded | 2.4 ft·lb/in | 130 J/m | |
| Flow : 73°F (23°C), 0.125 in (3.18 mm), Compression Molded | 2.0 ft·lb/in | 110 J/m | |
| Drop Impact Resistance | | | ASTM D4226 |
| 73°F (23°C) ³ | 1.48 in·lb/mil | 65.8 J/cm | |
| 73°F (23°C) ⁴ | 3.62 in·lb/mil | 161 J/cm | |
| Hardness | Typical Value (English) | Typical Value (SI) | Test Method |
| Durometer Hardness (Shore D, 15 sec) | 83 | 83 | ASTM D2240 |
| Thermal | Typical Value (English) | Typical Value (SI) | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |
| 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm) | 160 °F | 71.1 °C | |
| CLTE - Flow | 3.6E-5 in/in/°F | 6.4E-5 cm/cm/°C | ASTM D696 |
| Flammability | Typical Value (English) | Typical Value (SI) | Test Method |
| Flame Rating | | | UL 94 |
| 0.030 in (0.75 mm), ALL | V-0 | V-0 | |
| 0.06 in (1.5 mm), ALL | 5VA | 5VA | |
| Additional Information | Typical Value (English) | Typical Value (SI) | |
| Ease of Sizing | Good | Good | |

Note: NSF listings are obtained on specific colors. Contact PolyOne for the latest listing of approved colors for this product.
 Note: The Cell Classification was determined using the notched Izod test with injection molded samples.

Processing Information

| Extrusion | Typical Value (English) | Typical Value (SI) |
|------------------|-------------------------|--------------------|
| Melt Temperature | 360 to 380 °F | 182 to 193 °C |

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

³ Procedure A, C.125 Dart

⁴ Procedure B, C.125 Dart



Beyond Polymers.

Better Business Solutions.™