



OnFlex™ BIO 5370A-E0004

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™-Bio 5300 series thermoplastic elastomer compounds are soft thermoplastic polyurethane compounds made from renewable natural sources. These compounds contain at least 20% of renewable material as certified according to ASTM-D6866. The OnFlex™-Bio 5300 series compounds are formulated to provide an excellent surface finish, soft-touch haptic, abrasion resistance and mechanical properties.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Abrasion Resistant	• Good Scratch Resistance	• Renewable Resource Content
Uses	• Automotive Applications	• Consumer Applications	• General Purpose
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Calendering • Extrusion	• Injection Molding • Multi Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.05 g/cm ³	1.05 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Abrasion Loss	63.0 mm ³	63.0 mm ³	DIN 53516
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ²			DIN 53504
Across Flow : 100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	479 psi	3.30 MPa	
Flow : 100% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	551 psi	3.80 MPa	
Tensile Stress ²			DIN 53504
Across Flow : 300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	1150 psi	7.90 MPa	
Flow : 300% Strain, 73°F (23°C), 0.0787 in (2.00 mm)	1330 psi	9.20 MPa	
Tensile Stress ²			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1600 psi	11.0 MPa	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	1840 psi	12.7 MPa	
Tensile Elongation ²			DIN 53504
Across Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	410 %	410 %	
Flow : Break, 73°F (23°C), 0.0787 in (2.00 mm)	410 %	410 %	
Tear Strength ³			ISO 34-1
Across Flow : 73°F (23°C), 0.0787 in (2.00 mm)	245 lbf/in	42.9 kN/m	
Flow : 73°F (23°C), 0.0787 in (2.00 mm)	270 lbf/in	47.2 kN/m	

Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Compression Set			ISO 815
73°F (23°C), 72 hr	51 %	51 %	
158°F (70°C), 22 hr	73 %	73 %	
212°F (100°C), 22 hr	84 %	84 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness (Shore A)	70	70	ISO 868
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Odor Rating ⁴	3.0	3.0	VDA 270

Properties are measured using injection molded plaques.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	212 to 248 °F	100 to 120 °C
Drying Time	1.0 to 2.0 hr	1.0 to 2.0 hr
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Fast	Fast

Notes

¹ Typical values are not to be construed as specifications.

² Type 1, 7.9 in/min (200 mm/min)

³ Method A, Trouser

⁴ Method A3



Beyond Polymers.

Better Business Solutions.™