



OnFlex™ S KE 70A-3E1726 Black UV SO10

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™-S KE thermoplastic elastomer compounds are based on hydrogenated styrenic block copolymers. This range of compounds are specially compatibilized to provide excellent adhesion to a variety polar substrates including PC, ABS, PC/ABS, ASA and PVC. OnFlex-S KE compounds can be processed by 2K molding or overmolding, insert moulding or co-extrusion.

General

| | | | |
|-----------------------|--|--|-----------------|
| Material Status | • Commercial: Active | | |
| Regional Availability | • Africa & Middle East • Asia Pacific | • Europe • Latin America | • North America |
| Features | • Good Adhesion | • Good Mold Release | • UV Resistant |
| Uses | • Automotive Applications • Consumer Applications | • Industrial Applications • Overmolding | |
| RoHS Compliance | • RoHS Compliant | | |
| Appearance | • Black | | |
| Forms | • Pellets | | |
| Processing Method | • Coextrusion | • Multi Injection Molding | |

Technical Properties ¹

| Physical | Typical Value (English) | Typical Value (SI) | Test Method |
|-----------------------------|--|--|-------------|
| Density | 1.15 g/cm ³ | 1.15 g/cm ³ | ISO 1183 |
| Melt Volume-Flow Rate (MVR) | 40 cm ³ /10min | 40 cm ³ /10min | ISO 1133 |
| Elastomers | Typical Value (English) | Typical Value (SI) | Test Method |
| Tensile Stress (Break) | 812 psi | 5.60 MPa | ISO 37 |
| Tensile Elongation (Break) | 350 % | 350 % | ISO 37 |
| Hardness | Typical Value (English) | Typical Value (SI) | Test Method |
| Shore Hardness (Shore A) | 70 | 70 | ISO 868 |
| Additional Information | Typical Value (English) | Typical Value (SI) | |
| Generic Material Type | Styrenic Thermoplastic Elastomer (TES) | Styrenic Thermoplastic Elastomer (TES) | |

Properties are measured using injection molded plaques. Compression Set values are for parts annealed for 24 hours at 100°C.

Processing Information

| Injection | Typical Value (English) | Typical Value (SI) |
|------------------------|-------------------------|--------------------|
| Drying Temperature | 212 °F | 100 °C |
| Drying Time | 2.0 hr | 2.0 hr |
| Processing (Melt) Temp | 392 to 446 °F | 200 to 230 °C |
| Mold Temperature | 68 to 104 °F | 20 to 40 °C |
| Injection Rate | Slow-Moderate | Slow-Moderate |

Notes

¹ Typical values are not to be construed as specifications.